

SolarRoll PE 55

(Formerly Solartech PE55)

Multi-purpose Polyester Laminate

Product Information Leaflet

SolarRoll PE 55 is a UV Curing GRP (Glass Re-inforced Plastic) Laminate containing high grade Isophthalic polyester resins, fillers and glass re-inforcements which has been formulated to ensure excellent protection against corrosion, abrasion, impact and aggressive climatic environments.

SolarRoll PE 55 is suitable for use on a wide range of substrates including steel, concrete, GRP, FRP, PVC glass and wood. The product is supplied on rolls and in its un-cured state is a soft, malleable, easy to use material ready for application. The material can be easily cut to any shape using knives or scissors. Once fully cured SolarRoll PE 55 also provides top quality fire retardancy and low smoke emissions if exposed to flame.

SolarRoll PE 55 is highly recommended for use as protection to all types of insulation and also as a non-metallic cladding product. Extensive testing has been carried out to confirm conformance to offshore Fire and Smoke regulations.

The ability to offer user friendly, one component, fast curing, seamless on site applications has attracted many clients to use the SolarTech UV Curing technology.

Typical Applications:

- All types of Insulation Protection
- Storage Tanks
- Pipe Support Protection
- Roofs
- Flooring
- Water and Weatherproofing
- General maintenance

And many others....



SolarRoll PE 55 (Formerly Solartech PE55)

Product Data																																																												
Appearance	Sheet Lamination																																																											
Colour	Grey																																																											
Mix Ratio	One Component																																																											
Curing Mechanism	Ultra Violet (UV). Natural or UV Lamp																																																											
Material Thickness	Standard 1.8mm(70mils). Available range: 1.5mm-2.5mm (60-100mils)																																																											
Weight	2.9kg/m ² Standard																																																											
Packaging	Standard Roll 10mtr x 1mtr and 10mtr x 600mm																																																											
Technical Data																																																												
	<table border="1"> <thead> <tr> <th>Typical Values</th> <th>Test Method</th> </tr> </thead> <tbody> <tr> <td>Tensile strength</td> <td>55 Mpa (7970 psi)</td> <td>BS 2782 - 1994</td> </tr> <tr> <td>Flexural strength</td> <td>> 130 Mpa (>18,800 psi)</td> <td>ASTM D790 - 03</td> </tr> <tr> <td>Flexural Modulus</td> <td>5.98 Gpa (8.6x10⁵ psi)</td> <td>ASTM D2344</td> </tr> <tr> <td>Elongation at break</td> <td>> 3%</td> <td>BS 2782 - 1994</td> </tr> <tr> <td>Coeff. Of Thermal expansion</td> <td>2.9 10⁻⁵ Degree C</td> <td>ASTM D696-03</td> </tr> <tr> <td>Impact resistance</td> <td>> 60 Kj/sqm</td> <td>BS EN ISO 180</td> </tr> <tr> <td>Hardness</td> <td>> 60 Barcol</td> <td>ASTM D2583-01</td> </tr> <tr> <td>Compression strength</td> <td>> 200 Mpa (29,000 psi)</td> <td>ASTM D695-2002a</td> </tr> <tr> <td>Adhesion to steel</td> <td>> 14 Mpa (>2000 psi)</td> <td>ASTM D4541-02</td> </tr> <tr> <td>Water Vapour Permeability</td> <td>0.28g/m²/24h/mmHg (0.18perm)</td> <td>ASTM E96</td> </tr> <tr> <td>Heat distortion</td> <td>> 145 Deg C (>293 F)</td> <td>ASTM D648</td> </tr> <tr> <td>Fire rating</td> <td colspan="2">ASTM E84 CLASS A, BS 476pt 7 CLASS 1, IMO RESOLUTION MSC307 (88)(2010FTP CODE) ANNEX 1: PART 2 & PART 5</td> </tr> <tr> <td>Flash Point</td> <td>> 32 Deg C (> 90F)</td> <td>ASTM D93</td> </tr> <tr> <td>Heat resistance</td> <td>Wet: 90 deg C (195F)</td> <td>Dry: 200 Deg C (390F)</td> </tr> <tr> <td>Chemical resistance</td> <td colspan="2">Good. Chemical resistance chart available on request</td> </tr> <tr> <td>Electrical Properties</td> <td colspan="2">Dielectric strength: 9KV/mm as per IEC 243</td> </tr> <tr> <td>Arc resistance:</td> <td colspan="2">greater than 180 seconds as per ASTM D495</td> </tr> <tr> <td>Tracking resistance:</td> <td colspan="2">greater than 600 volts as per IEC 112</td> </tr> <tr> <td>Insulation resistance:</td> <td colspan="2">10 to the power of 13 ohms as per IEC 93</td> </tr> </tbody> </table>	Typical Values	Test Method	Tensile strength	55 Mpa (7970 psi)	BS 2782 - 1994	Flexural strength	> 130 Mpa (>18,800 psi)	ASTM D790 - 03	Flexural Modulus	5.98 Gpa (8.6x10 ⁵ psi)	ASTM D2344	Elongation at break	> 3%	BS 2782 - 1994	Coeff. Of Thermal expansion	2.9 10 ⁻⁵ Degree C	ASTM D696-03	Impact resistance	> 60 Kj/sqm	BS EN ISO 180	Hardness	> 60 Barcol	ASTM D2583-01	Compression strength	> 200 Mpa (29,000 psi)	ASTM D695-2002a	Adhesion to steel	> 14 Mpa (>2000 psi)	ASTM D4541-02	Water Vapour Permeability	0.28g/m ² /24h/mmHg (0.18perm)	ASTM E96	Heat distortion	> 145 Deg C (>293 F)	ASTM D648	Fire rating	ASTM E84 CLASS A, BS 476pt 7 CLASS 1, IMO RESOLUTION MSC307 (88)(2010FTP CODE) ANNEX 1: PART 2 & PART 5		Flash Point	> 32 Deg C (> 90F)	ASTM D93	Heat resistance	Wet: 90 deg C (195F)	Dry: 200 Deg C (390F)	Chemical resistance	Good. Chemical resistance chart available on request		Electrical Properties	Dielectric strength: 9KV/mm as per IEC 243		Arc resistance:	greater than 180 seconds as per ASTM D495		Tracking resistance:	greater than 600 volts as per IEC 112		Insulation resistance:	10 to the power of 13 ohms as per IEC 93	
Typical Values	Test Method																																																											
Tensile strength	55 Mpa (7970 psi)	BS 2782 - 1994																																																										
Flexural strength	> 130 Mpa (>18,800 psi)	ASTM D790 - 03																																																										
Flexural Modulus	5.98 Gpa (8.6x10 ⁵ psi)	ASTM D2344																																																										
Elongation at break	> 3%	BS 2782 - 1994																																																										
Coeff. Of Thermal expansion	2.9 10 ⁻⁵ Degree C	ASTM D696-03																																																										
Impact resistance	> 60 Kj/sqm	BS EN ISO 180																																																										
Hardness	> 60 Barcol	ASTM D2583-01																																																										
Compression strength	> 200 Mpa (29,000 psi)	ASTM D695-2002a																																																										
Adhesion to steel	> 14 Mpa (>2000 psi)	ASTM D4541-02																																																										
Water Vapour Permeability	0.28g/m ² /24h/mmHg (0.18perm)	ASTM E96																																																										
Heat distortion	> 145 Deg C (>293 F)	ASTM D648																																																										
Fire rating	ASTM E84 CLASS A, BS 476pt 7 CLASS 1, IMO RESOLUTION MSC307 (88)(2010FTP CODE) ANNEX 1: PART 2 & PART 5																																																											
Flash Point	> 32 Deg C (> 90F)	ASTM D93																																																										
Heat resistance	Wet: 90 deg C (195F)	Dry: 200 Deg C (390F)																																																										
Chemical resistance	Good. Chemical resistance chart available on request																																																											
Electrical Properties	Dielectric strength: 9KV/mm as per IEC 243																																																											
Arc resistance:	greater than 180 seconds as per ASTM D495																																																											
Tracking resistance:	greater than 600 volts as per IEC 112																																																											
Insulation resistance:	10 to the power of 13 ohms as per IEC 93																																																											
Application Data																																																												
	Please refer to the SolarTech Sheet Lamine ' Information for Use ' leaflet. Available from your Solartech agent or from Solartech web site www.solartechuv.com																																																											
Handling / Storage																																																												
Working life	Vigilant care should be taken to shield SolarRoll PE 55 from direct sunlight or UV lamps during application as this will greatly reduce the working life of the material.																																																											
Environment	Under no circumstances should SolarRoll PE 55 be applied in wet conditions or on wet substrates.																																																											
Safety Precautions	Please refer to the product Material Safety Data Sheets for detailed information on handling, shipping and disposal.																																																											
Storage	Store in cool, dry conditions (not more than 25 Deg C (77 Deg F). Avoid storage near any heat source or sunlight. Always store material in its original packing in a horizontal position.																																																											
Shelf Life	18 months when stored as per manufacturers instructions.																																																											



SolarTech
International Limited
P.O. Box 54992
Dubai Airport Free Zone,
Dubai, United Arab Emirates
Tel: + 971 4 6091932 Fax: + 971 4 6091933
email: info@solartechuv.com
web: www.solartechuv.com

SOLARTECH Agent:



Plastic World Solutions GmbH
Nürnbergstrasse 15
90522 OBERASBACH
GERMANY
info@plasticworldsolutions.com
www.plasticworldsolutions.com

Note: SolarRoll PE55 is a product of Solartech International Ltd BVI company. This product is **EXCLUSIVELY** manufactured Under Licensed by Greentech Thermal Insulation Products Manufacturing LLC, U.A.E.

DISCLAIMER : The information contained herein is to the best of our knowledge accurate and is given in good faith without warranty. Users are deemed to have satisfied themselves independently as to the suitability of our products for their particular purpose. In no event shall SolarTech International Limited be liable for consequent or incidental damages.